

TECHNICAL DATA SHEET

IsoCast URS 7017

IsoCast URS 7017 is a product developed for repairing cracks in concrete.

APPLICATIONS

Concrete Crack Fill

*Values given are not intended to be used in specific preparation

Component Properties	
Color - ISO	brown
Color - POL	gray
Specific Gravity - 74°F, ISO	1.01
Specific Gravity - 74°F, POL	.952
Viscosity - ASTM D-2196 - 74°F, ISO	11 cps
Viscosity - ASTM D-2196 - 74°F, POL	5 cps
% Solids	56 %
Reactivity Profile	
Ratio by Weight - ISO:POL	1.16 - 1
Ratio by Volume - ISO:POL	1 - 1
Pot Life - 100g	1 Minute
Gel Time - 100 gram sample, 74°F	200 Seconds
Demold Time	24 Hours
Typical Physical Properties	
Hardness - ASTM D2240 - Shore D	68 Shore D
Tear Strength - ASTM D624, Die C	127 pli
Tensile Modulus - ASTM D412	133000 psi
Tensile Strength - ASTM D412	3572 psi
Elongation - ASTM D412	3 %

RECOMMENDED HANDLING INSTRUCTIONS

-use only in well-ventilated areas.

-wear chemically resistant rubber gloves, safety glasses, and an apron.

-avoid prolonged or repeated contact with skin.

-In case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.

-In case of eye contact, flush eyes with water for 15 minutes and consult a physician.

-If swallowed or comes into contact with eyes, seek medical attention immediately.

STORAGE

Protect Iso and Poly side from moisture. If the Iso side material is exposed to moisture, including moisture from the air, it will release CO2 gas. If placed in a sealed container, this gas can cause a dangerous build up of pressure potentially resulting in injury or death. If the Poly side is exposed to excess moisture and then applied it may cause weak or foamed material to be applied.

Always mix/roll Poly side prior to use to ensure a homogenous product.

Protect from moisture. If the Iso side material is exposed to moisture, including moisture from the air, it will release CO2 gas.

SAFETY

-Refer to the product SDS for all relevant safety information.

Date Modified 1/9/2019

Since Seller exercises no control over Buyers application or use of the product manufactured by Seller ("product") and since materials used with the product may vary, it is understood that:

THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTIES OR MECHANTABILITY OR FOR ANY PARTICULAR PURPOSE. While
all data presented in Seller's technical data sheet is based on the best information available to Seller and believed correct, such data is not to be construed
as a warranty that the product will conform to such specifications. Such technical data sheets are subject to change without notice. Reported laboratory
test results of fire redundancy in no way relates to the actual performance under fire conditions. Since all urethane systems are organic, they will burn.
Reported laboratory test results of the color stability in no way relates to the actual performance upon exposure to light sources. Since all aromatic
urethanes experience color degradation upon ultraviolet light exposure, Seller shall not be liable for any damages resulting from ultraviolet light color
degradation of any aromatic urethane systems manufactured or sold by Seller.

• The liability of the Seller shall not exceed the purchase price and the Buyer shall not be entitled to nor the Seller be liable for any consequential, incidental, indirect or special damages resulting in any manner from the furnishing of the product.

www.isotecintl.com	"The Chemistry Behind Performance"®	(800) 234-6300
--------------------	-------------------------------------	----------------