

## IsoFlex 750

IsoFlex 750 is a two-component, semi-flexible polyurethane foam system. It is designed for molding applications where good flow characteristics and even density distributions (without defects such as voids or blisters) are desired.

\*Values given are not intended to be used in specific preparation

### Component Properties

Color - ISO	Dark Brown
Color - POL	Brown
Specific Gravity - 74°F, ISO	1.23
Specific Gravity - 74°F, POL	1.03
Viscosity - ASTM D-2196 - 74°F, ISO	200 cps
Viscosity - ASTM D-2196 - 74°F, POL	2000 cps

### Reactivity Profile

Ratio by Weight - ISO:POL	60 - 100
Cream Time	13 Seconds
Gel Time	100 Seconds
Rise Time	150 Seconds
Tack Free Time	140 Seconds

### Typical Physical Properties

Free Rise Density - ASTM D1622	5.75 - 6.25 pcf
--------------------------------	-----------------

### RECOMMENDED HANDLING INSTRUCTIONS

- use only in well-ventilated areas.
- wear chemically resistant rubber gloves, safety glasses, and an apron.
- avoid prolonged or repeated contact with skin.
- In case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.
- In case of eye contact, flush eyes with water for 15 minutes and consult a physician.
- If swallowed or comes into contact with eyes, seek medical attention immediately.

### STORAGE

#### Storage:

Protect Iso and Poly side from moisture. If the Iso side material is exposed to moisture, including moisture from the air, it will release CO<sub>2</sub> gas. If placed in a sealed container, this gas can cause a dangerous build up of pressure potentially resulting in injury or death. If the Poly side is exposed to excess moisture and then applied it may cause weak or foamed material to be applied.

Always mix/roll Poly side prior to use to ensure a homogenous product.

### SAFETY

- Refer to the product SDS for all relevant safety information.

Date Modified 5/14/2015

Since Seller exercises no control over Buyers application or use of the product manufactured by Seller (“product”) and since materials used with the product may vary, it is understood that:

- THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTIES OR MECHANABILITY OR FOR ANY PARTICULAR PURPOSE. While all data presented in Seller’s technical data sheet is based on the best information available to Seller and believed correct, such data is not to be construed as a warranty that the product will conform to such specifications. Such technical data sheets are subject to change without notice. Reported laboratory test results of fire redundancy in no way relates to the actual performance under fire conditions. Since all urethane systems are organic, they will burn.
- Reported laboratory test results of the color stability in no way relates to the actual performance upon exposure to light sources. Since all aromatic urethanes experience color degradation upon ultraviolet light exposure, Seller shall not be liable for any damages resulting from ultraviolet light color degradation of any aromatic urethane systems manufactured or sold by Seller.
- The liability of the Seller shall not exceed the purchase price and the Buyer shall not be entitled to nor the Seller be liable for any consequential, incidental, indirect or special damages resulting in any manner from the furnishing of the product.

[www.isotecintl.com](http://www.isotecintl.com)

“The Chemistry Behind Performance”®

(800) 234-6300

---